

**AMENDMENTS TO THE CLAIMS**

1. (Previously Presented) A process for sealing and insulating a fuel cell plate, the process comprising:  
  
    providing a gas impermeable fuel cell plate having first and second surfaces;  
    applying a coating precursor on at least the first surface of the fuel cell plate, the coating precursor adapted to polymerize in response to radiation; and  
    exposing the coating precursor on the fuel cell plate to radiation to initiate polymerization.
2. (Original) The process of claim 1, wherein the coating precursor is applied by screen printing.
3. (Original) The process of claim 1, wherein the coating precursor is exposed to ultraviolet radiation.
4. (Original) The process of claim 3, wherein the coating precursor is successively exposed to ultraviolet radiation of at least two different wavelengths.
5. (Original) The process of claim 1, wherein the coating precursor is exposed to infrared radiation.
6. (Original) The process of claim 1, wherein the coating precursor is adapted to polymerize in response to ultraviolet radiation.
7. (Original) The process of claim 1, wherein the coating precursor is adapted to polymerize in response to electron beam radiation.

8. (Original) The process of claim 1, wherein the coating precursor is adapted to polymerize in response to infrared radiation.
9. (Original) The process of claim 1, wherein the coating precursor is exposed to radiation for about less than about 45 minutes.
10. (Original) The process of claim 1, wherein the coating precursor is exposed to radiation for about less than about one minute.
11. (Original) The process of claim 1, wherein the coating precursor is exposed to radiation for about less than about 30 seconds.
12. (Original) The process of claim 1, wherein the coating precursor is exposed to radiation for about less than about 15 seconds.
13. (Original) The process of claim 1, wherein the coating precursor is exposed to radiation for about less than about 5 seconds.
14. (Original) The process of claim 1, wherein the coating precursor is an ultraviolet-curable coating precursor.
15. (Original) The process of claim 1, wherein the coating precursor is an electron beam-curable coating precursor.
16. (Original) The process of claim 1, wherein the coating precursor is an infrared-curable coating precursor.

17. (Previously Presented) A process for sealing and insulating a fuel cell plate, the process comprising:

providing a gas impermeable fuel cell plate having first and second surfaces;  
applying a coating precursor on at least the first surface of the fuel cell plate, the coating precursor adapted to polymerize in response to ultraviolet radiation; and  
exposing the coating precursor on the fuel cell plate to ultraviolet radiation to initiate polymerization, wherein the coating precursor includes an acrylated oligomer and a photoinitiator.

18. (Original) The process of claim 17, wherein the coating precursor further includes a mono-functional monomer for reducing viscosity.

19. (Original) The process of claim 17, wherein the coating precursor further includes a multi-functional monomer for increasing cross-link density.

20. (Original) The process of claim 17, wherein the coating precursor further includes an adhesion promoter.

21. (Original) The process of claim 17, wherein the coating precursor further includes an air-release agent.

22. (Previously Presented) An insulated fuel cell plate comprising:

a gas impermeable plate having first and second surfaces; and  
a coating precursor applied on at least one of the first and second surfaces of the plate, the coating precursor adapted to polymerize in response to radiation.

23. (Original) The insulated fuel cell plate of claim 22, wherein the coating precursor is less than about 250  $\mu$  thick.
24. (Original) The insulated fuel cell plate of claim 22, wherein the coating precursor is less than about 150  $\mu$  thick.
25. (Original) The insulated fuel cell plate of claim 22, wherein the coating precursor is adapted to polymerize in response to ultraviolet radiation.
26. (Original) The insulated fuel cell plate of claim 22, wherein the coating precursor is adapted to polymerize in response to electron beam radiation.
27. (Original) The insulated fuel cell plate of claim 22, wherein the coating precursor is adapted to polymerize in response to infrared radiation.
28. (Original) The insulated fuel cell plate of claim 22, wherein the coating precursor is substantially polymerized after exposure to radiation for about less than about 45 minutes.
29. (Original) The insulated fuel cell plate of claim 22, wherein the coating precursor is substantially polymerized after exposure to radiation for about less than about one minute.
30. (Original) The insulated fuel cell plate of claim 22, wherein the coating precursor is substantially polymerized after exposure to radiation for about less than about 30 seconds.
31. (Original) The insulated fuel cell plate of claim 22, wherein the coating precursor is substantially polymerized after exposure to radiation for about less than about 15 seconds.

32. (Original) The insulated fuel cell plate of claim 22, wherein the coating precursor is substantially polymerized after exposure to radiation for about less than about 5 seconds.

33. (Previously Presented) An insulated fuel cell plate comprising:

a gas impermeable plate having first and second surfaces; and

a coating precursor applied on at least one of the first and second surfaces of the plate, polymerized in response to radiation and wherein the coating precursor is an acrylate resin, an epoxy nitrile resin, or an organopolysiloxane, either alone or in combination.

34. (Original) The insulated fuel cell plate of claim 33, wherein the coating precursor includes an acrylated urethane oligomer and a photoinitiator.

35. (Original) The insulated fuel cell plate of claim 34, wherein the coating precursor further includes a mono-functional monomer for reducing viscosity.

36. (Original) The insulated fuel cell plate of claim 34, wherein the coating precursor further includes a multi-functional monomer for increasing cross-link density.

37. (Original) The insulated fuel cell plate of claim 34, wherein the coating precursor further includes an adhesion promoter.

38. (Original) The insulated fuel cell plate of claim 34, wherein the coating precursor further includes an air-release agent.

39. (Original) An insulated fuel cell plate comprising:
- a plate having first and second surfaces; and
  - a coating precursor applied on at least one of the first and second surfaces of the plate, the coating precursor comprising:
    - an acrylated aliphatic urethane oligomer;
    - an acrylated epoxy oligomer;
    - a mono-functional monomer for reducing viscosity of the coating precursor;
    - a multi-functional monomer for increasing cross-link density;
    - an adhesion promoter; and
    - a photoinitiator.
40. (Original) The insulated fuel cell plate of claim 39, wherein the mono-functional monomer is isobornyl acrylate monomer.
41. (Original) The insulated fuel cell plate of claim 39, wherein the adhesion promoter is a methacrylated polyol.
42. (Original) The insulated fuel cell plate of claim 39, wherein the multi-functional monomer is propoxylated glycerol triacrylate monomer.
43. (Original) The insulated fuel cell plate of claim 39, wherein the photoinitiator is a blend of 1-phenyl-2-hydroxy-2-methyl-1-propanone and benzophenone.
44. (Original) The insulated fuel cell plate of claim 39, wherein the coating precursor further comprises an air-release agent.
45. (Original) The insulated fuel cell plate of claim 44, wherein the air-release agent is a polydimethyl siloxane.

46. (Currently Amended) An ultraviolet radiation curable coating precursor ~~for coating that~~ is applied on a non-metallic substrate, comprising:

- an acrylated aliphatic urethane oligomer;
- an acrylated epoxy oligomer;
- a mono-functional monomer for reducing viscosity of the coating precursor;
- a multi-functional monomer for increasing cross-link density;
- an air release agent;
- an adhesion promoter; and
- a photoinitiator.

47. (Original) The ultraviolet radiation-curable coating precursor of claim 46, wherein the mono-functional monomer is isobornyl acrylate monomer.

48. (Cancelled)

49. (Original) The ultraviolet radiation-curable coating precursor of claim 46, wherein the multi-functional monomer is propoxylated glycerol triacrylate monomer.

50. (Original) The ultraviolet radiation-curable coating precursor of claim 46, wherein the photoinitiator is a blend of 1-phenyl-2-hydroxy-2-methyl-1-propanone and benzophenone.

51. (Canceled)

52. (Previously Presented) The ultraviolet radiation-curable coating precursor of claim 46, wherein the air-release agent is a polydimethyl siloxane.

53. (Currently Amended) An ultraviolet radiation-curable coating precursor ~~for coating~~ that is applied to a non-metallic substrate comprising:

from about 25 wt. % to about 65 wt. % of an acrylated aliphatic urethane oligomer;

from about 5 wt. % to about 20 wt. % of an acrylated epoxy oligomer;

from about 20 wt. % to about 40 wt. % of a mono-functional monomer for reducing viscosity of the coating precursor;

from about 1 wt. % to about 5 wt. % of a multi-functional monomer for increasing cross-link density;

from about 1 wt. % to about 15 wt. % of an adhesion promoter;

from about 0.1 wt. % to about 10 wt. % of a photoinitiator; and

an air release agent.

54. (Original) The ultraviolet radiation-curable coating precursor of claim 53, wherein the mono-functional monomer is isobornyl acrylate monomer.

55. (Canceled)

56. (Original) The ultraviolet radiation-curable coating precursor of claim 53, wherein the multi-functional monomer is propoxylated glycerol triacrylate monomer.

57. (Original) The ultraviolet radiation-curable coating precursor of claim 53, wherein the photoinitiator is a blend of 1-phenyl-2-hydroxy-2-methyl-1-propanone and benzophenone.

58. (Canceled)

59. (Previously Presented) The ultraviolet radiation-curable coating precursor of claim 53, wherein the air-release agent is a polydimethyl siloxane.

60. (Previously Presented) An ultraviolet radiation curable coating precursor, comprising:



an acrylated aliphatic urethane oligomer;  
an acrylated epoxy oligomer;  
a mono-functional monomer for reducing viscosity of the coating precursor;  
a multi-functional monomer for increasing cross-link density;  
an adhesion promoter; and  
a photoinitiator,  
wherein the adhesion promoter is a methacrylated polyol.

61. (Previously Presented) An ultraviolet radiation-curable coating precursor comprising:  
from about 25 wt. % to about 65 wt. % of an acrylated aliphatic urethane oligomer;  
from about 5 wt. % to about 20 wt. % of an acrylated epoxy oligomer;  
from about 20 wt. % to about 40 wt. % of a mono-functional monomer for reducing  
viscosity of the coating precursor;  
from about 1 wt. % to about 5 wt. % of a multi-functional monomer for increasing cross-  
link density;  
from about 1 wt. % to about 15 wt. % of an adhesion promoter; and  
from about 0.1 wt. % to about 10 wt. % of a photoinitiator,  
wherein the adhesion promoter is a methacrylated polyol.